

# Tyfo® TC Epoxy Tack Coat

## DESCRIPTION

Tyfo® TC Epoxy is a two-component, solvent-free, NSF-Certified epoxy matrix material specially formulated to provide improved adhesion of the Tyfo® Fibrwrap System to vertical and overhead applications. Please refer to the NSF Listing for the NSF-61 Listed Application.

## USE

Tyfo® TC is recommended for use in special applications where Tyfo® S or WS Epoxy will not provide adequate adhesion between the fabric and substrate. Typical examples for use are overhead or vertical surfaces, undersides of beams when applying composite materials, horizontal or vertical surfaces where excellent adhesion to a substrate is necessary for maximum strength, wall surfaces, and any surface where bonding between fabric and substrate is critical. Tyfo® TC can also be used to improve the bond between successive layers of the Tyfo® Fibrwrap® System.

## ADVANTAGES

- Excellent adhesive properties
- NSF-Listed Product
- Good high temperature properties
- Good low temperature properties
- Long working time (1-2 hours)
- High elongation
- Ambient cure

## COVERAGE

One unit of Tyfo® TC Epoxy will cover approximately 30 to 75 sq. ft. (2.8 to 7m<sup>2</sup>) of surface area at a thickness of 1/16" (2mm). The existing condition of the surface as well as the temperatures of both the epoxy and application surface will significantly affect the coverage estimation.

## PACKAGING

Order in pre-measured units in five-gallon containers.

## MIX RATIO

100.0 parts of component A to 29.4 parts of component B by volume. (100 parts of component A to 23.3 parts of component B by weight.)

## SHELF LIFE

Two years in original, unopened and properly stored container.

## STORAGE CONDITIONS

Store epoxy at 40° to 90°F (4° to 32°C). Avoid freezing. Store in a cool place. Temporary storage of these components should not be in high temperatures, particularly the "A" component. The lids of both components should be kept tightly sealed.

4/12 Tyfo® TC

## CERTIFICATE OF COMPLIANCE

- Will be supplied upon request, complete with state and federal packaging laws with copy of labels used.
- Material safety data sheets will be supplied upon request.

## HOW TO USE THE TYFO® TC EPOXY

### INSTALLATION

Tyfo® System to be installed by Fyfe Co. LLC trained and certified applicators. Installation shall be in strict compliance with the Fyfe Co. LLC Quality Control Manual.

### SURFACE PREPARATION

The required surface preparation is largely dependent on the type of element being strengthened. In general, the surface must be clean, dry and free of protrusions or cavities, which may cause voids behind the Tyfo® composite. Discontinuous wrapping surfaces (walls, beams, slabs, etc.) typically require a light sandblast, grinding or other approved methods to prepare for bonding. If waterblasting is used, allow a sufficient amount of time for adequate drying prior to application of epoxies. Anchors are incorporated in some designs. The

Fyfe Co. LLC engineering staff will provide the proper specifications and details based on the project requirements.

### MIXING

For pre-measured units in 5-gallon containers, pour the contents of component B into the pail of component A. Mix ratio: 100.0 parts of component A to 29.4 parts of component B by volume (100 parts of component A to 23.3 parts of component B by weight). Do not thin; solvents will prevent proper cure. Mix thoroughly for five minutes with a Tyfo® low speed mixer at 400-600 RPM until components are thoroughly dispersed. Excessive mixing will shorten pot life.

### APPLICATION

Apply a prime coat of Tyfo® S or WP Epoxy to the prepared surface and allow to tack. Apply Tyfo® TC Epoxy with a roller, trowel or non-porous float.

Note: Avoid applying layers thicker than 1/16" (2mm) as this will not provide additional tackiness. If the Tyfo® TC Epoxy begins to set up before the fabric can be applied, scrape off and apply freshly mixed Tyfo® TC Epoxy and allow to tack prior to the application of the fabric. Please refer to the NSF Listing for the NSF-61 Listed Application.

EPOXY COMPONENT PROPERTIES		
Curing Schedule 72 hours post cure at 140°F (60°C)		
PROPERTY	ASTM TEST METHOD	TYPICAL TEST VALUE*
Mix Ratio, by volume		100:29.4
Color		Translucent Beige
Viscosity, cps		
Component A		180,000
Component B		200
Component A & B		55,000
Gel Time, 150 grams		250 minutes
Thin Film Set		14 - 16 hours
Bond Strength		
Dry Concrete		Excellent
Compressive Strength		4,088 psi
Tensile Strength	D638	3,285 psi (22.7 MPa)
Tensile Modulus	D638	174,000 psi (1.2 GPa)
Tensile Elongation	D638	1.88%
Flexural Strength	D790	6,645 psi (45.8 MPa)
Flexural Modulus	D790	178,000 psi (1.23 GPa)
T <sub>g</sub>	E1356	160°F (71°C)

Testing temperature: 70° F (21° C) Crosshead speed: 0.5 in. (13mm)/min. Grips Instron 2716-0055 - 30 kips  
 \* Specification values can be provided upon request.

## SET UP TIME

Tyfo® TC Epoxy is formulated to give a minimum of 1 to 2 hours working time. Cooler temperatures will usually extend and warmer temperatures shorten the working time.

## LIMITATIONS

Application temperature of the epoxy is a minimum 40° F (4° C) and maximum of 100° F (38° C). DO NOT THIN, solvents will prevent proper cure.

## CAUTION!

### COMPONENT A - Irritant:

Prolonged contact to the skin may cause irritation. Avoid eye contact.

### COMPONENT B - Irritant:

Corrosive. Contact with skin may cause severe burns. Avoid eye contact. Product is a strong sensitizer. Use of safety goggles and chemical resistant gloves recommended. Remove contaminated clothing. Avoid breathing vapors. Use adequate ventilation. Use of an organic vapor respirator recommended.

## SAFETY PRECAUTIONS

Avoid breathing vapors. Avoid contact with eyes and skin. Use of an approved respirator with an organic absorption cartridge is recommended for possible vapors. Rubber gloves, rubber boots, and protective suits are recommended for handling and application of this material. Safety glasses or a face shield are recommended to prevent eye contact.

## FIRST AID

In case of skin contact, wash thoroughly with soap and water. For eye contact, flush immediately with plenty of water; contact physician immediately. For respiratory problems, remove to fresh air. Wash clothing before reuse.

## CLEANUP

Collect with absorbent material, flush with water. Dispose of in accordance with local disposal regulations. Uncured material can be removed with approved solvent. Cured materials can only be removed mechanically.

## SHIPPING LABELS CONTAIN

- State specification number with modifications, if applicable
- Component designation
- Type, if applicable
- Manufacturer's name
- Date of manufacture
- Batch name
- State lot number, if applicable
- Directions for use
- Warnings or precautions required by law

**KEEP CONTAINER TIGHTLY CLOSED.  
NOT FOR INTERNAL CONSUMPTION.  
CONSULT MATERIAL SAFETY DATA SHEET  
(MSDS) FOR MORE INFORMATION.  
KEEP OUT OF REACH OF CHILDREN.  
FOR INDUSTRIAL USE ONLY.**

# Fyfe Co. LLC

Tyfo® Fibrwrap® Systems

8380 Miralani Drive, San Diego, CA 92126

Tel: 858.642.0694 Fax: 858.444.2982

E-mail: [info@fyfeco.com](mailto:info@fyfeco.com) [www.fyfeco.com](http://www.fyfeco.com)

**Statement of Responsibility:** The technical information and application advice in this publication is based on the present state of our best scientific and practical knowledge. As the nature of the information herein is general, no assumption can be made as to the product's suitability for a particular use or application, and no warranty as to its accuracy, reliability or completeness, either expressed or implied, is given other than those required by State legislation. The owner, his representative or the contractor is responsible for checking the suitability of products for their intended use. Field service, where provided, does not constitute supervisory responsibility. Suggestions made by the Fyfe Co., either verbally or in writing, may be followed, modified or rejected by the owner, engineer or contractor since they, and not the Fyfe Co., are responsible for carrying out procedure appropriate to a specific application.