

Tyfo[®] UC Composite Laminate Strip System

DESCRIPTION

Tyfo[®] UC Composite Laminate Strip System is comprised of a high modulus, high tensile strength, pull-formed, epoxy-carbon composite adhered to the primed substrate with thickened Tyfo[®] S Epoxy, Tyfo[®] TC Epoxy, Tyfo[®] TC-1 Epoxy or Tyfo[®] MB-3 Adhesive.

USE

For reinforcing of general building construction, industrial buildings, parking structures, bridges and other structures constructed of concrete, wood and steel.

ADVANTAGES

- Class 1 rating per ASTM E84.
Flame spread: 25 Smoke developed: 140
- Good high temperature properties
- Good low temperature properties
- Consistent material properties
- Ease of installation
- Pull-formed composites do not contain releasing agents that affect material properties
- High tensile modulus and strength
- 100% epoxy matrix

COVERAGE

Surface area coverage for the Tyfo[®] UC Composite Laminate Strip System is dependent on the width and length ordered (see "Available Widths and Thicknesses for Tyfo[®] UC Composite Laminate Strips"). One unit of Tyfo[®] TC Epoxy or thickened Tyfo[®] S Epoxy will cover approximately 30 to 75 sq. ft. (2.8 to 7m²) of surface area at a thickness of 1/16" (2mm). One unit of Tyfo[®] MB-3 Epoxy will cover approximately 10 - 25 sq. ft. (0.93 - 2.3m²) of surface area at 1/16" (2mm) thick. The existing condition of the surface as well as the temperatures of both the epoxy and application surface will significantly affect the coverage estimation.

PACKAGING

The Tyfo[®] UC Composite Laminate Strips are available in any length. Standard rolls come in 100, 250 and 500 foot (30.48m, 76.2m, and 152.4m) lengths. The rolls are approximately 36" (914mm) inside diameter. Typically ships in 40" x 40" x 6" (1016mm x 1016mm x 152mm) boxes. Tyfo[®] TC Epoxy pre-measured units ship in 5-gallon (18.9L) containers. See Tyfo[®] epoxy data sheets for more information.

MIX RATIO

See Tyfo[®] epoxy data sheets for mix ratio information.

SHELF LIFE

Epoxy - one year in original, unopened and properly stored containers.
Strips - ten years in proper storage conditions.

STORAGE CONDITIONS

Store the Tyfo[®] UC Composite Laminate Strips and epoxy at 40° to 90° F (4° to 32° C) and epoxy at 40° to 90° F (4° to 32° C). Avoid freezing. Store rolls flat, not on ends, at temperatures below 100° F (38° C). Avoid moisture and water contamination.

CERTIFICATE OF COMPLIANCE

- Will be supplied upon request, complete with state and federal packaging laws with copy of labels used.
- Material safety data sheets will be supplied upon request.

HOW TO USE

THE TYFO[®] UC COMPOSITE LAMINATE STRIP SYSTEM

DESIGN

Tyfo[®] UC Composite Laminate Strip System shall be designed to meet specific design criteria. The criteria for each project is dictated by the engineer of record and any relevant building codes and/or guidelines. The design should be based on the allowable strain for each type of application and the design modulus of the material. The Fyfe Co. LLC engineering staff will provide preliminary design at no obligation.

INSTALLATION

Tyfo[®] UC Composite Laminate Strip System shall be installed by Fyfe Co. LLC trained and certified applicators. Installation shall be in strict compliance with the Fyfe Co. LLC Quality Control Manual.

SURFACE PREPARATION

The surface to receive the Tyfo[®] UC Composite Laminate Strip System must be sound and prepared for bonding by means of abrasive methods. Typically, light sandblasting, grinding or other approved methods are acceptable. The surface should be free of protrusions or cavities. The Fyfe Co. LLC engineering staff will provide the proper specifications and details based on the project requirements. Bond strength to substrate can be verified by ASTM D-4541.

MIXING

See Tyfo[®] epoxy data sheets for mix ratio and mixing instructions.

APPLICATION

Apply a prime coat of Tyfo[®] S Epoxy to the prepared substrate. Apply a 1/16" (2mm) layer of Tyfo[®] Epoxy to the substrate prior to applying the the Tyfo[®] UC Composite Laminate Strip System. Clean abraded side (side without lettering and without glossy appearance) of Strip with acetone or similar approved solvent to remove any foreign debris and let stand for 30 minutes minimum to allow for evaporation of the solvent. Apply a 1/16" (2mm) minimum thickness layer of Tyfo[®] epoxy adhesive to the cleaned side of Strip. Allow sufficient time for the epoxy to reach maximum tackiness. Apply the Strip within the specified cure time of the Tyfo[®] epoxy. The Tyfo[®] UC Composite Laminate Strip System to be applied uniformly, meeting all specifications.

TYPICAL DRY FIBER PROPERTIES

Tensile Strength	711,000 psi (4.9 GPa)
Tensile Modulus	33.4 x 10 ⁶ psi (230 GPa)
Ultimate Elongation	2.1%
Density	0.065 lbs./in. ³ (1.8 g/cm ³)
Volumetric Fiber Content	62%

COMPOSITE GROSS LAMINATE PROPERTIES

PROPERTY	ASTM METHOD	TYPICAL TEST VALUE	DESIGN VALUE*
Ultimate tensile strength in primary fiber direction, psi	D3039	405,000 psi (2.79 GPa)	364,500 psi (2.51 GPa)
Elongation at break	D3039	1.8%	1.67%
Tensile Modulus, psi	D3039	22.5 x 10 ⁶ psi (155 GPa)	20.25 x 10 ⁶ psi (139.6 GPa)
Layer Thickness**		Varies	Varies

* Design and specification values will vary based on individual project requirements and applicable safety factors. Contact Fyfe Co. LLC engineers to determine appropriate specification values.

** See "Available widths and thicknesses for the Tyfo[®] UC Composite Laminate Strips."

AVAILABLE WIDTHS AND THICKNESSES FOR TYFO® UC COMPOSITE LAMINATE STRIPS

Thickness: 0.075" (1.9mm) or 0.055" (1.4mm) *
Widths: 2.0" (50.8mm) 4.0" (101.6mm) *

* Other thicknesses and widths are available.

DESIGNATIONS

The Tyfo® UC Composite Laminate Strip System is designated by the width then the thickness in mils. Example - 2" wide, 0.055-inch laminate would be designated as "2UC55."

LIMITATIONS

Application temperature of the epoxy is a minimum 40° F (4° C) and maximum of 100° F (38° C). DO NOT THIN, solvents will prevent proper cure.

CAUTION!

COMPONENT A - Irritant:

Prolonged contact to the skin may cause irritation. Avoid eye contact.

COMPONENT B - Irritant:

Corrosive. Contact with skin may cause severe burns. Avoid eye contact. Product is a strong sensitizer. Use of safety goggles and chemical resistant gloves recommended. Remove contaminated clothing. Avoid breathing vapors. Use adequate ventilation. Use of an organic vapor respirator recommended.

LAMINATE PRECAUTIONS

Use caution when uncoiling roll. Use of an approved particle mask is recommended for possible airborne particles. Gloves are recommended when handling strips to avoid skin irritation. Safety glasses are recommended to prevent eye irritation.

FIRST AID

In case of skin contact, wash thoroughly with soap and water. For eye contact, flush immediately with plenty of water; contact physician immediately. For respiratory problems, remove to fresh air. Wash clothing before reuse.

CLEANUP

Collect with absorbent material, flush with water. Dispose of in accordance with local disposal regulations. Uncured material can be removed with approved solvent. Cured materials can only be removed mechanically.

SHIPPING LABELS CONTAIN

- State specification number with modifications, if applicable
- Component designation
- Type, if applicable
- Manufacturer's name
- Date of manufacture
- Batch name
- State lot number, if applicable
- Directions for use
- Warnings or precautions required by law

**NOT FOR INTERNAL CONSUMPTION.
CONSULT MATERIAL SAFETY DATA SHEET
(MSDS) FOR MORE INFORMATION.
KEEP OUT OF REACH OF CHILDREN.
FOR INDUSTRIAL USE ONLY.**

Fyfe Co. LLC

Tyfo® Fibrwrap® Systems

3940 Ruffin Road, Suite C, San Diego, CA 92123

Tel: 858.642.0694 Fax: 858.444.2982

E-mail: info@fyfeco.com www.fyfeco.com

Statement of Responsibility: The technical information and application advice in this publication is based on the present state of our best scientific and practical knowledge. As the nature of the information herein is general, no assumption can be made as to the product's suitability for a particular use or application, and no warranty as to its accuracy, reliability or completeness, either expressed or implied, is given other than those required by State legislation. The owner, his representative or the contractor is responsible for checking the suitability of products for their intended use. Field service, where provided, does not constitute supervisory responsibility. Suggestions made by the Fyfe Co., either verbally or in writing, may be followed, modified or rejected by the owner, engineer or contractor since they, and not the Fyfe Co., are responsible for carrying out procedure appropriate to a specific application.